



Technical Data Sheet

ATI 904L™

Stainless Steel: Superaustenitic

(UNS N08904)

INTRODUCTION

ATI 904L™ alloy (UNS N08904) is an austenitic stainless steel designed for a middle to high level of corrosion resistance. The alloy contains high levels of chromium and nickel with additions of molybdenum and copper to provide added corrosion resistance in certain media. The alloy is produced to low carbon levels for use in the welded condition as in welded vessels and other large and complex fabrications.

The high nickel (25%) and molybdenum (4.5%) contents of the ATI 904L™ alloy provide good resistance to chloride stress corrosion cracking, although not total resistance as judged by the extremely severe laboratory test, boiling magnesium chloride. The Chromium, molybdenum and nickel levels provide general and chloride pitting corrosion resistance above the level of Types 316 and 317 in many media. The copper addition provides added resistance to reducing media such as hot phosphoric acid and dilute sulfuric acid.

The N08904 alloy has been incorporated in ASTM and ASME specifications, and is widely and readily available in a variety of product forms, welding electrodes, and fittings. The ATI 904L™ alloy has performed well in a variety of service environments such as utility scrubbers, acid and fertilizer production. Representative corrosion data follow.

COMPOSITION

Element	Typical	ASTM Specification (Alloy N08904)
Carbon	0.015	0.020 maximum
Manganese	1.60	2.00 maximum
Phosphorus	0.035	0.045 maximum
Sulfur	0.003	0.035 maximum
Silicon	0.50	1.00 maximum
Chromium	20.50	19.00-23.00
Nickel	24.5	23.00-28.00
Molybdenum	4.50	4.00-5.00
Copper	1.50	1.00-2.00
Iron	Remainder*	Remainder*

*By difference.

CORROSION RESISTANCE

General Corrosion

The alloy content of the ATI 904L™ alloy provides a level of general corrosion resistance that is generally higher than familiar Type 316 stainless steel. Illustrative laboratory corrosion data from boiling solutions are listed below.



Technical Data Sheet

Boiling Solution	Corrosion Rate in MPY (mm/a)	
	ATI 316™	ATI 904L™
20% Acetic Acid	0.1 (<0.01)	0.6 (0.02)
45% Formic Acid	10.9 (0.28)	7.7 (0.20)
1% Hydrochloric Acid	226 (5.74)	21.6 (0.55)
10% Oxalic Acid	40.1 (1.02)	27.1 (0.69)
20% Phosphoric Acid	0.20 (<.01)	0.5 (0.01)
10% Sodium Bisulfate	41.5 (1.06)	8.9 (0.23)
50% Sodium Hydroxide	>100 (>2.5)	9.6 (0.24)
10% Sulfamic Acid	63.6 (1.62)	9.1 (0.23)
10% Sulfuric Acid	636 (16.2)	101 (2.57)

Pitting Corrosion

The ATI 904L alloy contains a combination of chromium and molybdenum which produces an improved level of resistance to pitting and crevice corrosion by chlorides compared to ATI 316 stainless steel. The alloy may be considered for such end uses as tubeshells in seawater heat exchangers or pulp and paper bleach plant equipment where a level of resistance above that of 316 is desired but some degree of attack can be tolerated. The ATI 904L alloy is not totally resistant to environments such as aerated seawater.

Resistance to chloride ion pitting or crevice corrosion can be ranked in laboratory tests such as 10% Ferric Chloride (ASTM Procedure G-48). In this test, the material is tested with artificial crevices attached, and test temperature is raised after each test period in which no attack is observed. Failure is noted as that temperature at which attack is first observed, called the onset temperature for crevice corrosion attack. In this manner, a series of alloys may be ranked as follows:

Alloy	Temperature of Onset of Crevice Corrosion Attack*	
	°F	(°C)
ATI 316™	27	(-3)
ATI 317™	35	(2)
ATI 904L™	65	(18)
AL-6XN™	113	(45)
ATI 625™	113	(45)
AL 29-4C®	125	(52)

*ASTM Procedure G-48, 10% Ferric Chloride Solution.

Chloride Stress Corrosion Cracking

Resistance to chloride stress corrosion cracking is correlated with nickel content, with the 25% nickel ATI 904L™ alloy, showing improved resistance compared to an 8% nickel alloy like Type 304 stainless steel. Resistance of the ATI 904L™ alloy is further aided by presence of 4.5% molybdenum. However, the alloy is not completely resistant to the extremely severe laboratory test, such as boiling magnesium or lithium chlorides, as shown by the following comparative data.

Boiling Solution	Performance Using U-Bend Samples and Test Times to 1000 Hours		
	ATI 316™	ATI 904L™	AL 20™
42% Magnesium Chloride	Fail	Fail	Fail
33% Lithium Chloride	Fail	Fail	Pass
26% Sodium Chloride	Fail	Pass	Pass

Fail = Chloride stress corrosion cracks observed. Pass = No cracking observed in testing.

Data are typical, are provided for informational purposes, and should not be construed as maximum or minimum values for specification or for final design, or for a particular use or application. The data may be revised anytime without notice. We make no representation or warranty as to its accuracy and assume no duty to update. Actual data on any particular product or material may vary from those shown herein. TM is trademark of and ® is registered trademark of ATI Properties, Inc. or its affiliated companies. © The starburst logo is a registered trademark of ATI Properties, Inc. © 2012 ATI. All rights reserved.

Allegheny Technologies Incorporated
1000 Six PPG Place
Pittsburgh, PA 15222-5479 U.S.A.
www.ATImetals.com



Technical Data Sheet

Galvanic Compatibility

The ATI 904L alloy may influence corrosion when galvanically coupled to less corrosion resistant materials in relatively high conductivity waters such as seawater. In such a case, the ATI 904L alloy, the noble metal, will cause galvanic corrosion of the less noble material. The ATI 904L alloy is sufficiently resistant that it may be considered as the tubesheet material for highly corrosion resistant tubing alloys in seawater.

Intergranular Corrosion

The low carbon level of the ATI 904L alloy provides resistance to intergranular corrosion in the welded condition as judged by laboratory intergranular corrosion rates. ASTM Procedure A708 or A262 Practice E are most commonly applied to the N08904 alloy. The following laboratory tests are illustrative. Corrosion rates are given in mils per year (MPY) and, in parentheses, millimeters per annum (mm/a):

Intergranular Corrosion Resistance Test Procedure	Corrosion, Rates Mils per Year, (mm/a)	
	ATI 316™	ATI 904L™
Copper-Copper Sulfate-16% Sulfuric Acid (ASTM A262 Practice E) Evaluated by Bend Test	No Fissures	No Fissures
Ferric Sulfate-Sulfuric Acid (ASTM A262 Practice B)	35.5 (0.90)	14.2 (0.36)
65% Nitric Acid (ASTM A262 Practice C)	34.3 (0.87)	15.4 (0.39)

PHYSICAL PROPERTIES

Density

0.287 lb/in³
7.95 g/m³

Specific Gravity

7.95

Specific Heat at 68°F (20°C)

0.11 BTU/lb-°F

Average Coefficient of Thermal Expansion

8.5 x 10 ⁻⁶ /°F (68- 212°F)	15.3 x 10 ⁻⁶ /°C (20-100°C)
9.2 x 10 ⁻⁶ /°F (68- 750°F)	16.5 x 10 ⁻⁶ /°C (20-400°C)
10.1 x 10 ⁻⁶ /°F (68-1475°F)	18.2 x 10 ⁻⁶ /°C (20-800°C)

Thermal Conductivity

	BTU/Ft-hr-°F	W/m•K
68°F (20°C)	6.6	11.5
212°F (100°C)	6.8	12.9
392°F (200°C)	8.8	15.2

Electrical Resistivity

95.2 microhm-cm at 68°F
99.0 microhm-cm at 200°F

Data are typical, are provided for informational purposes, and should not be construed as maximum or minimum values for specification or for final design, or for a particular use or application. The data may be revised anytime without notice. We make no representation or warranty as to its accuracy and assume no duty to update. Actual data on any particular product or material may vary from those shown herein. TM is trademark of and ® is registered trademark of ATI Properties, Inc. or its affiliated companies. © The starburst logo is a registered trademark of ATI Properties, Inc. © 2012 ATI. All rights reserved.

Allegheny Technologies Incorporated
1000 Six PPG Place
Pittsburgh, PA 15222-5479 U.S.A.
www.ATImetals.com



Technical Data Sheet

Magnetic Permeability

<1.02

Modulus of Elasticity

28 x 10⁶ psi
190 GPa

The thermal conductivity of the ATI 904L™ alloy is typical of the more highly alloyed austenitic stainless steels. Because of the high nickel content, no ferrite is expected in ATI 904L™ alloy and magnetic permeability is low, even for heavily cold deformed material.

MECHANICAL PROPERTIES

ASTM and ASME B&PVC Coverage

The alloy is covered by ASTM and ASME Boiler and Pressure Vessel Code Specifications as indicated here. Within those specifications, the alloy is designated UNS (Unified Numbering System) N08904.

Product Form	ASTM Specification	ASME Specification
Plate, Sheet and Strip	B 625	SB 625
Welded Pipe	B 673	SB 673
Welded Tube	B 674	SB 674
Seamless Pipe and Tube	B 677	SB 677
Bar and Wire	B 649	SB 649

Typical (and minimum) Mechanical Properties for annealed material are listed:

Property	Typical Value	ASTM and ASME Specified Properties
Yield Strength	39,500 psi 270 MPa	31,000 psi 220 MPa minimum
Tensile Strength	88,000 psi 605 MPa	71,000 psi 490 MPa minimum
Elongation (% in 2")	50	36 minimum
Reduction of Area (%)	55	None Specified
Hardness (Brinell)	150	
Rockwell B	79	70-90*

*Hardness values are shown for information only.

The ATI 904L™ alloy is covered in Section VIII of the ASME Boiler and Pressure Vessel Code with allowable stresses assigned as follows:

Maximum Metal Temperatures		Maximum Allowable Stress per ASME	
°F	°C	ksi	MPa
100	38	17.8	123
200	93	16.7	115
300	149	15.1	104
400	204	13.8	95
500	260	12.7	88
600	316	12.0	83
700	371	11.4	79

*Alloy UNS N08904

For welded pipe and tubing, a factor of 0.85 is applied.

Data are typical, are provided for informational purposes, and should not be construed as maximum or minimum values for specification or for final design, or for a particular use or application. The data may be revised anytime without notice. We make no representation or warranty as to its accuracy and assume no duty to update. Actual data on any particular product or material may vary from those shown herein. TM is trademark of and ® is registered trademark of ATI Properties, Inc. or its affiliated companies. © The starburst logo is a registered trademark of ATI Properties, Inc. © 2012 ATI. All rights reserved.

Allegheny Technologies Incorporated
1000 Six PPG Place
Pittsburgh, PA 15222-5479 U.S.A.
www.ATImetals.com



Technical Data Sheet

Impact Resistance

Annealed ATI 904L™ alloy shows impact behavior typical of an austenitic stainless steel, that is, excellent toughness even at sub-zero temperatures.

PRODUCT FORMS

Plate, Sheet and Strip

- Plate width to 96"
- Plate thickness 3/16" to 1"
- Sheet width to 48"
- Sheet thickness .025" to .133"
- Strip width to 24"
- Strip thickness .025" to .133"
- Other sizes on application

FORMABILITY

The ATI 904L™ alloy is capable of being formed like the standard austenitic stainless steels. The material is somewhat stronger than familiar ATI 304 and ATI 316 stainless and consequently requires higher loads to cause the material to deform.

WELDABILITY

An overmatched, that is, more highly alloyed austenitic filler is suggested, for the best corrosion properties in welds, as in the joint between two plates of ATI 904L™ alloy. However, a matching composition is commercially available. Overmatched fillers are customarily used in such corrosion resisting applications as fabricated utility scrubber components. The welds are ductile as expected when austenitic stainless steels are welded using highly alloyed fillers.

For environments which are mildly corrosive to the ATI 904L™ alloy, matching filler may be used satisfactorily.

For welds which are not subjected to corrosive environments, standard austenitic filler materials are used satisfactorily.

HEAT TREATMENT

The ATI 904L™ alloy should be annealed (solution treated) between 2000 and 2100°F (1095 and 1150°C) and quickly cooled.