



Technical Data Sheet

ATI NiTi SMA 2™ Alloy

INTRODUCTION

- Typically used in shape memory nickel titanium alloy devices and actuators
- Applicable industry standards: ASTM F2005, ASTM F2004, ASTM F2082
- Transformation temperature: Austenite finish (A_f) temperature range 75°C to 120°C
- (Determined in the fully solution annealed condition by DSC testing)

Table 1. Ingot Chemistry

Element	Typical maximum (unless noted otherwise) (weight %)
Nickel	53.0 to 56.0
Carbon	0.005
Cobalt	0.005
Copper	0.005
Chromium	0.005
Hydrogen	0.002
Iron	0.005
Niobium	0.005
Nitrogen + Oxygen	0.025
Titanium	Balance

Table 2. Physical Properties

Melting Point	1310°C (2390°F)
Density	6.45 g/cm ³ (0.234 lbs/in ³)
Electrical Resistivity	Austenite phase: ~80-100 μΩ-cm Martensite phase: ~70-80 μΩ-cm
Thermal Conductivity	Austenite phase: 0.18 watt/cm-°C Martensite phase: 0.085 watt/cm-°C
Thermal Expansion	Austenite: 11 x 10 ⁻⁶ /°C Martensite: ~6.6 x 10 ⁻⁶ /°C

MECHANICAL PROPERTIES

Table 3. Mechanical Properties

Ultimate strength	>155 Ksi (1070 MPa)
Elongation	≥10%

PRODUCT FORMS AVAILABLE

- Sheet: Nominal 0.020" to 0.125"T in widths up to 24" widths. Surface finish typically hot worked, blasted and pickled
- Plate: Nominal 0.126"T up to 0.250"T in widths up to 24" widths. Surface finish typically hot worked, blasted and pickled
- Rod: 0.1" to 2" diameters, amount of cold work, length and surface finish conditions vary depending on customer requirements

Data are typical, are provided for informational purposes, and should not be construed as maximum or minimum values for specification or for final design, or for a particular use or application. The data may be revised anytime without notice. We make no representation or warranty as to its accuracy and assume no duty to update. Actual data on any particular product or material may vary from those shown herein. U.S. and foreign patents; other patents pending. TM is trademark of and ® is registered trademark of ATI Properties, Inc. or its affiliated companies. © The starburst logo is a registered trademark of ATI Properties, Inc. © 2014 ATI. All rights reserved..

Allegheny Technologies Incorporated
1000 Six PPG Place
Pittsburgh, PA 15222-5479 U.S.A.
www.ATImetals.com



Technical Data Sheet

- Wire: 0.010" to 0.099" diameters, coil sizes, amount of cold work, and surface finish conditions vary depending on customer requirements
- Other forms and sizes available upon request